

TECHNICAL DATASHEET "SACB14"

REFERENCE: SACB14

Length: 50 m

Width: 50 cm

Tear-off perforation: every 50 cm

COMPOSITION:

2 layers of LDPE film, extruded and thermoformed (922 kg/m²)

CHARACTERISTICS:

DESIGNATION	VALUE	UNIT
Bubble height	4,5	mm ± 10%
Bubble diameter	12	mm
Quantity of bubbles per m ²	6600	bubbles/m ²
Area weight of bubble film	92	g/m ² ± 7,5%
Theoretical thickness	100	µm ± 7,5%
Longitudinal tensile strength	45	N/m
Transverse tensile strength	25	N/m
Puncture resistance	16	N
Color	Pink	
Lifetime	≥ 12	months
Surface resistivity (objective)	2,10 ¹⁰ to 5,10 ¹⁰	Ohm (Ref. ASTM D-527)
Unload time (objective)	0,8 to 0,9	Seconds (Ref MIL-B-81705 B)

RECYCLABILITY:

100% recyclable